

FAST DRY 35 | 95-912 SERIES

DESCRIPTION

One-component, interior / exterior industrial gloss oil alkyd

PRINCIPAL CHARACTERISTICS

- Fast drying properties
- High gloss topcoat
- Ideal for light industrial applications and commercial buildings
- VOC Compliant <2.8 lb/ gal
- Full color tinting capacity

COLOR AND GLOSS LEVEL

- Porcelain white, black, light gray, safety colors, custom colors
- Gloss

Note: Certain colors, especially red, orange, and yellow may require additional coats for adequate hiding, especially if applied over primers with a significant color contrast

BASIC DATA AT 68°F (20°C)

Data for product	
Number of components	One
Volume solids	50 ± 3%
VOC (Supplied)	max. 2.7 lb/US gal (approx. 329 g/l)
Recommended dry film thickness	1.0 - 2.0 mils (25 - 50 µm) depending on system
Theoretical spreading rate	802 ft ² /US gal for 1.0 mils (20.0 m ² /l for 25 µm)
Shelf life	At least 36 months when stored cool and dry

Notes:

- See ADDITIONAL DATA - Overcoating intervals
- See ADDITIONAL DATA - Curing time

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

- Coating performance is proportional to the degree of surface preparation. Refer to the application instructions for specific primers and intermediate coats for application and curing procedures. Ensure epoxies are free from amine blush prior to overcoating. All previous coats must dry and free of contaminants. Adhere to all minimum and maximum topcoat times for specific primers and intermediate coats. Aged epoxy coatings require abrading prior to applying the product. A test patch over unknown coatings is recommended.



FAST DRY 35 | 95-912 SERIES

Substrate temperature and application conditions

- Surface temperature during application should be between 50°F (10°C) and 120°F (49°C)
- Surface temperature during application should be at least 5°F (3°C) above dew point
- Ambient temperature during application and curing should be between 50°F (10°C) and 100°F (38°C)
- Relative humidity during application and curing should not exceed 85%

Warning

Removal of old paint by sanding, scraping or other means may generate dust or fumes which contain lead. EXPOSURE TO LEAD DUST OR FUMES MAY CAUSE ADVERSE HEALTH EFFECTS, ESPECIALLY IN CHILDREN OR PREGNANT WOMEN. Controlling exposure to lead or other hazardous substances requires the use of proper protective equipment, such as a properly fitted and approved (e.g., NIOSH approved) respirator and proper containment and cleanup. For additional information, contact the USEPA/Lead Information Hotline at 1-800-424-LEAD or the regional Health Canada office

SYSTEM SPECIFICATION

- Primers for ferrous metal: 6-208, 90-712, 94-258, 97-680
- Primers for CMU: 6-7, 6-15, AMERLOCK 400 BF
- Primers for concrete/masonry: 4-603, 17-921, AMERLOCK SERIES
- Primers for drywall: 6-2
- Primers for galvanized steel: 17-921, AMERLOCK SERIES
- Primers for wood: 1-70, 6-9, 6-809, 17-921

Note: Solvent wipe the surface of the epoxy prior to application. Allow the epoxy to dry achieve a dry through state. If the epoxy has cured greater than 3x the dry through time, abrade the surface prior to coating

INSTRUCTIONS FOR USE

- If material has skinned over, gently remove
- Strain to remove any skin particles prior to agitation
- Agitate with a power mixer for 1 – 2 minutes until completely dispersed. Ensure good off-bottom mixing

Application

- Area should be sheltered from airborne particulates and pollutants
- Avoid combustion gases or other sources of carbon dioxide that may promote ambering of light colors
- Ensure good ventilation during application and curing
- Provide shelter to prevent wind from affecting spray patterns

Material temperature

Material temperature during application should be between 50°F (10°C) and 90°F (32°C)



FAST DRY 35 | 95-912 SERIES

Air spray

- Use standard conventional equipment
- Ensure there is a moisture and oil trap in the main air line

Recommended thinner

No thinner should be added

Nozzle orifice

Approx. 0.070 in (1.8 mm)

Nozzle pressure

Atomizing pressure 55 - 70 p.s.i. (4.0 - 5.0 bar); Fluid pressure 20 - 30 p.s.i. (1.5 - 2.0 bar)

Airless spray

- 30:1 pump or larger

Recommended thinner

No thinner should be added

Nozzle orifice

0.013 - 0.015 in (approx. 0.33 - 0.38 mm)

Brush/roller

- Use a high quality natural bristle brush and/or solvent resistant, 1/4" or 3/8" nap roller. Ensure brush/roller is well loaded to avoid air entrainment. Multiple coats may be necessary to achieve adequate film-build

Recommended thinner

No thinner should be added

Cleaning solvent

THINNER 21-06 (97-727)

ADDITIONAL DATA

Overcoating interval for DFT up to 2.0 mils (51 µm)				
Overcoating with...	Interval	50°F (10°C)	70°F (21°C)	90°F (32°C)
itself	Minimum	Less than 1 hour or after 3 days	Less than 1 hour or after 3 days	Less than 1 hour or after 3 days
	Maximum	Unlimited	Unlimited	Unlimited



FAST DRY 35 | 95-912 SERIES

Curing time for DFT up to 2.0 mils (51 µm)		
Substrate temperature	Dry to touch	Dry to handle
50°F (10°C)	1.5 hours	4 hours
70°F (21°C)	20 minutes	90 minutes
90°F (32°C)	12 minutes	50 minutes

DISCLAIMER

- For industrial or professional use only

SAFETY PRECAUTIONS

- For paint and recommended thinners see INFORMATION SHEETS 1430, 1431 and relevant Material Safety Data Sheets
- This is a solvent-borne paint and care should be taken to avoid inhalation of spray mist or vapor, as well as contact between the wet paint and exposed skin or eyes

Danger

Rags, steel wool or waste soaked with this product may spontaneously catch fire if improperly discarded. Immediately after use, place rags, steel wool or waste in a sealed water-filled metal container. Refer to www.pittsburghpaints.com, Spontaneous Combustion Advisory for additional information

WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective and Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

REFERENCES

- | | | |
|--|-------------------|------|
| • CONVERSION TABLES | INFORMATION SHEET | 1410 |
| • EXPLANATION TO PRODUCT DATA SHEETS | INFORMATION SHEET | 1411 |
| • SAFETY INDICATIONS | INFORMATION SHEET | 1430 |
| • SAFETY IN CONFINED SPACES AND HEALTH SAFETY, EXPLOSION HAZARD – TOXIC HAZARD | INFORMATION SHEET | 1431 |

WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

FAST DRY 35 | 95-912 SERIES

LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at www.ppgpmc.com. The English text of this sheet shall prevail over any translation thereof.

AVAILABILITY

Packaging

1-gallon and 5-gallon kits

Product codes	Description
95-9000	Neutral base*
95-901	Safety Red
95-9012	White base
95-902	Safety Yellow
95-903	Safety blue
95-904	Safety green
95-905	Safety Orange
95-909	Light Gray
95-912	Porcelain White
95-913	Black

Note: * Must be tinted before use. Tint with PERFORMACOLOR® colorants

The PPG logo, and all other PPG marks are property of the PPG group of companies. All other third-party marks are property of their respective owners.

