

PPG AQUACOVER™ ONE 645

DESCRIPTION

One-component, waterborne acrylic dispersion finish

PRINCIPAL CHARACTERISTICS

- Finish for interior accommodations, machinery spaces and engine rooms
- Particularly suitable when solvents are not permitted because of health and safety reasons
- Fast-drying and recoatable
- Good weather resistance
- Good color retention
- Allows safer working during hull outfitting of new-buildings

COLOR AND GLOSS LEVEL

- White (other colors available on request)
- Gloss

BASIC DATA AT 20°C (68°F)

Data for product	
Number of components	One
Mass density	1.2 kg/l (10.0 lb/US gal)
Volume solids	44 ± 2%
VOC (Supplied)	Directive 2010/75/EU, SED: max. 4.0 g/kg; 25 g/l
Recommended dry film thickness	50 - 100 µm (2.0 - 4.0 mils) per coat
Theoretical spreading rate	8.0 m ² /l for 50 µm (321 ft ² /US gal for 2.0 mils)
Dry to touch	1 hour
Overcoating Interval	Minimum: 12 hours Maximum: Unlimited
Shelf life	At least 24 months when stored cool and dry

Notes:

- See ADDITIONAL DATA – Overcoating intervals
- See ADDITIONAL DATA – Curing time

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

Substrate conditions

- Compatible previous coat must be dry and free from any contamination



PPG AQUACOVER™ ONE 645

Substrate temperature and application conditions

- Substrate temperature during application should be at least 10°C (50°F)
 - Substrate temperature during application should be at least 3°C (5°F) above dew point
 - Relative humidity during application should not exceed 75%
-

INSTRUCTIONS FOR USE

- Stir well before use
 - The temperature of the paint should preferably be above 15°C (59°F), otherwise extra thinner may be required to obtain application viscosity
 - Too much tap water results in reduced sag resistance
 - Adequate ventilation must be maintained during application and curing
 - Must be protected from freezing at all times during storage and/or transport
-

Air spray

Recommended thinner

Tap water

Volume of thinner

5 - 10%, depending on required thickness and application conditions

Nozzle orifice

1.8 - 2.0 mm (approx. 0.070 - 0.079 in)

Nozzle pressure

0.3 - 0.4 MPa (approx. 3 - 4 bar; 44 - 58 p.s.i.)

Airless spray

Recommended thinner

Tap water

Volume of thinner

0 - 5%, depending on required thickness and application conditions

Nozzle orifice

Approx. 0.46 - 0.53 mm (0.018 - 0.021 in)

Nozzle pressure

12.0 - 15.0 MPa (approx. 120 - 150 bar; 1741 - 2176 p.s.i.)

PPG AQUACOVER™ ONE 645

Brush/roller

- Long haired brush or polyether roller with rounded edges

Recommended thinner

Tap water

Volume of thinner

0 – 5%

Cleaning solvent

- Tap water and THINNER 40-25
- Please contact your PPG representative for availability in your region

CLEANING PROCEDURE

- Pulsator filter and tip filter must be taken out of the equipment and cleaned properly
- The following tables illustrate the cleaning procedure of the spray equipment when changing from spraying with solvent- borne paint to waterborne paints (table 1) and from waterborne paints to solvent-borne paints (table 2)

Table of cleaning procedure

Table 1: Cleaning procedure from solvent-borne to waterborne paints

Steps	Text
1st cleaning	THINNER 90-53
2nd cleaning	THINNER 40-25
3rd cleaning	With warm tap water of 30°C (86°F) to 35°C (95°F) after which waterborne paints can be sprayed

Table 2: Cleaning procedure from waterborne to solvent-borne paints

Steps	Text
1st cleaning	Warm tap water of 30°C (86°F) to 35°C (95°F)
2nd cleaning	THINNER 40-25
3rd cleaning	THINNER 90-53



PPG AQUACOVER™ ONE 645

ADDITIONAL DATA

Overcoating interval for DFT up to 75 µm (3.0 mils)				
Overcoating with...	Interval	10°C (50°F)	20°C (68°F)	30°C (86°F)
itself	Minimum	16 hours	12 hours	8 hours
	Maximum	Unlimited	Unlimited	Unlimited

Note:

- Surface must be dry and free from any contamination

SAFETY PRECAUTIONS

- Although this is a waterborne paint, care should be taken to avoid inhalation of spray mist, as well as contact between the wet paint and exposed skin or eyes
- See Safety Data Sheet and product label for complete safety and precaution requirements

WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective & Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

REFERENCES

- Information sheet | Explanation of product data sheets
- Guide | PPG SIGMACARE PLUS | Online guide to maintenance at sea

WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at www.ppgpmc.com. The English text of this sheet shall prevail over any translation thereof.

The PPG logo, and all other PPG marks are property of the PPG group of companies. All other third-party marks are property of their respective owners.