

JP35x Series

2.1 VOC Multi Purpose Primer (National Rule)

Background

SHOP-LINE® JP35x series is a fast drying, two component, low VOC primer-sealer which may be used as a primer surfacer or as a wet-on-wet sealer when integrated with clear coat. JP35x Series is available in white, gray and black.

Components

Primer

JP354 2.1 VOC Multi-Purpose Primer
- White
JP355 2.1 VOC Multi-Purpose Primer
- Gray
JP356 2.1 VOC Multi-Purpose Primer
- Black

Hardener

JH358 Multi-Purpose Primer
Hardener

Reducer

JR505 Fast Reducer
JR506 Medium Reducer
JR507 Slow Reducer
JR508 Very Slow Reducer
(refer to SLTB-001NR *Shop-Line*
National Rule Thinner Guide)
JR554 Low VOC Compliant Reducer
(Fast)
JR555 Low VOC Compliant Reducer
(Medium)
JR556 Low VOC Compliant Reducer
(Slow)

Clearcoats

Any JC Series Clearcoat

Compatible Products

Can be applied over:

Cleaned sanded and etch primed steel, galvanized and aluminum.
Sanded and cleaned body filler, SMC and gel-coated fiberglass.
Properly cleaned and sanded E-Coat
Cleaned, cured and sanded OEM and refinish coatings.
JP209 Gray Polyester Primer Filler
JP310 Chrome Free Etch Primer
JP37x Epoxy Primer Series

Can be topcoated with:

JP37x Epoxy Primer Series
JP33x 2K Urethane Sealer Series
JB *Shop-Line* Basecoat
JBP Acrylic Urethane Basecoat
JE Acrylic Enamel
JAU Direct Gloss Acrylic Urethane

Compatible Products

Surface Cleaning:

JX101 Wax and Grease Remover
JX992 Plastic Cleaner
SWX350 H₂O-SO-CLEAN® Waterborne Pre-Cleaner

Sanding

For use as a primer: 180-220 Grit machine on bare steel
For use as a sealer: 320-400 Grit machine on primer or old finishes.

Mixing



Primer Surfacer:	JP35x	:	JH358	:	JR50x/JR55x
	4	:	1	:	2



Wet on Wet Sealer:	JP35x	:	JC Series Clear	:	JH358	:	JR50x/JR55x
	3	:	1	:	1	:	1



Pot Life: 1/2 Hour at 70°F (21°C) at 4:1:2
1 Hour at 70°F (21°C) at 3:1:1:1



Additives: JX993 Flex Additive 10% to RTS mix
SL87 Extender 5% to RTS mix

Air Pressure and Gun Setup



HVLP: 8 - 10 psi at the air cap
Compliant: 29 - 40 psi at the gun

Gun Setup: 1.3 - 1.6 mm or equivalent

Note: For best overall results, refer to spraygun manufacturer's recommendations for inlet air pressures.

Application



Coats:	4:1:2	2 - 4 coats for Primer-Surfacer
	3:1:1:1	1 - 2 coats for Wet-on-Wet Sealer

Dry Times



Between Coats: 5 - 10 minutes at 70°F (21°C)



Air Dry: **4:1:2 Primer Surfacer**
1-2 hours at 70°F (21°C) to sand and topcoat
3:1:1:1 Wet on Wet Sealer
15 minutes to topcoat



Force Dry: **4:1:2 Primer Surfacer**
20 - 30 minutes at 140°F (61°C) metal temperature



IR (Medium): **4:1:2 Primer Surfacer**
10 - 15 minutes



Topcoat: **Air Dry**
4:1:2 Primer Surfacer
1-2 hours to sand and topcoat
3:1:1:1 Wet on Wet Sealer
15 minutes to topcoat
Force Dry
4:1:2 Primer Surfacer
After cool down

Clean Up

Clean spray guns, gun cups, storage pots, etc., thoroughly with JR reducers, JT571 0.21 VOC General Purpose Solvent or another appropriate clean up solvent after each use. Follow EPA guidelines for proper storage and disposal of solvent-borne waste paint.

Properties

Film Build Per Coat

Applied 3:1:1:1 1.2 - 1.5 mils.

Applied 4:1:2 1.5 - 2 mils.

Square foot coverage at 1 mil

Applied 3:1:1:1 605 - 669 sq. ft. / gal. at 100% transfer

Applied 4:1:2 553 - 595 sq. ft. / gal. at 100% transfer

PRIMER - PRIMER SEALER	Standard System	Flexible System	Standard System	Flexible System
RTS Combinations	JP35x : JH358 : JR50x/JR55x	JP35x : JH358 : JR50x/JR55x + 10% JX993	JP35x : JC620/ JC630 : JH358 : JR50x/JR55x	JP35x : JC6700/ JC6800 : JH358 : JR50x/JR55x + 10% JX993
Volume Ratio:	4 : 1 : 2	4 : 1 : 2 +10%	3 : 1 : 1 : 1	3 : 1 : 1 : 1 +10%
Applicable Use Category	Primer	Primer	Primer - Sealer	Primer - Sealer
VOC Regulatory (less water less exempt) (g/L)	406 - 458	417 - 463	379 - 418	392 - 428
VOC Regulatory (less water less exempt) (lbs/gal)	3.39 - 3.82	3.48 - 3.86	3.16 - 3.49	3.27 - 3.57
Solids wt. %	50.0 - 54.5	49.8 - 54.1	51.3 - 56.5	51.0 - 55.8
Solids vol. %	34.5 - 37.0	34.9 - 37.1	37.7 - 41.9	37.8 - 41.7
Sq. Ft. Coverage at 1 mil at 100% transfer efficiency	553 - 594	560 - 595	605 - 672	606 - 669

Limitations

Shop-Line products should not be combined with components of other product lines.

Precautionary Information:

The contents of this package may have to be blended with other components before the product can be use. Before opening the packages be sure you understand the warning messages on the labels of all components since the mixture will have the hazards of all of its parts. Spray equipment must be handled with due care and in accordance with manufacturer's recommendations. Follow label directions for respirator use. Wear eye and skin protection. Observe all applicable precautions.

EMERGENCY MEDICAL OR SPILL CONTROL INFORMATION (412) 434-4515; IN CANADA (514)-645-1320

See Safety Data Sheet and Labels for additional safety information and handling instructions.

Data Safety Sheets for the PPG products mentioned in this publication are available through your PPG *Shop-Line* brand distributor. To the best of our knowledge, the technical information in this bulletin is accurate; however, since PPG Industries is constantly improving its coating and paint formulas, the current technical data may vary somewhat from what was available when this bulletin was printed. Contact your *Shop-Line* brand distributor or visit www.ppgrefinish.com for the most up-to-date information.

